

Features



50 micron Chrome effect PET film



Permanent & Clear adhesive



Double-side PE Coated Liner



Up to 1 years durability



Applications

- | | |
|--|---|
| <input type="checkbox"/> Outdoor Signage | <input type="checkbox"/> Window |
| <input checked="" type="checkbox"/> Indoor Signage | <input type="checkbox"/> Smooth Wall |
| <input type="checkbox"/> Vehicle Wraps | <input type="checkbox"/> Textured Wall |
| <input type="checkbox"/> Vehicle slight curve | <input type="checkbox"/> LSE (PP, PE, ABS) |
| <input type="checkbox"/> Back-lit | <input checked="" type="checkbox"/> Signboard (Lettering) |

Product	Color
LC5110	Chrome Silver
LC5111	Brusehd Chrome Silver
LC5120	Chrome Gold
LC5121	Brushed Chrome Gold



Printers

- Solvent Inkjet
- Latex Inkjet
- UV Inkjet
- Screen Printing
- Not Printable



Roll Sizes

- 92 cm (36in)
- 105cm (41in)
- 110cm (43in)
- 122cm (48in)
- 127cm (50in)
- 137cm (54in)
- 152cm (60in)
- 155cm (61in)
- 160cm (63in)

Physical Properties

Property	Specification	Test Method
Thickness (Including adhesive)	75 μ m \pm 10%	Micrometer
Tensile strength	\geq 1.8kg/cm	ASTM 882
Elongation	\leq 100%	ASTM 882
Peel adhesion(24hrs)	\geq 1,200g/in	180 peeling PSTC-1
Application temp.	\geq 10 $^{\circ}$ C	18 to 25 $^{\circ}$ C optimum, on clean substrate
Gloss	-	@60, in Machine Direction (ASTM D 2457)
Dimensional Stability	Max 0.5mm	Adhered to Aluminum Plate, Length Direction (100 $^{\circ}$ C Oven, 2hr , Average)
Release liner thickness	0.14mm \pm 10%	Micrometer

The information provided on this sheet represents typical properties and does not constitute a specification. No liability will be accepted for errors and omissions and in no circumstances shall LG Hausys Ltd be liable for any loss or injury arising directly or as a consequence of the publication of this data sheet. All LG Hausys vinyl sold subject to our conditions of sale. LG Hausys also retains the right to change sizes and specifications of products without prior notice.

■ Recommendation



Shelf life

Shelf life is 12 months from factory shipment.
Storage condition: Free from excessive moisture, temperature, direct sunlight (20 °C x 50% R.H)



Durability

Durability is based on unprinted film vertical exposure
Please see Durability guide of LG Hausys (www.lghausys.com)



Converting Method

Cutting

- Electro cut/Hand cut/Kiss cut/Die cut
⇒ These factors can affect cutting and weeding quality
- Weight on the knife: Slightly notch the liner.
- Sharpness of the knife blade: Dull knives creates a serrated look to cut edge of the film
⇒ LG recommends vinyl weeding takes place soon after cutting (Within 1 Hour).

If weeding is delayed too long and if the temperature is too high, the adhesive layer could “reseat” itself and could hinder the ease of weeding.



Compatible Products


- LG Hausys' Flexible sign faces (Flex)
- LG Hausys' Application Tape (LC2000)

■ Durability Guide



Durability Period & Exposure Conditions

Exposure to	Durability period		Examples (1 year product, Zone 1&2)
	Zone 1 & 2	Zone 3	
Vertical	100%	50%	1 year × 100% = 1 year
Non-Vertical	60%	30%	1 year × 60% = 0.6 year
Horizontal	30%	15%	1 year × 30% = 0.3 year



Please refer to LG Hausys durability guide of zone 1,2 and 3. (Zone system chart)

www.lghausys.com